



FISA TEHNICA SPUMA POLIURETANICA POLYURETHAN FOAM TECHNICAL DATA SHEET



Tip de spuma / Foam grade:	N3535K (N35140)	Clasa spuma : N; D; L; E
Culori / Colours:	Alb / White	D
Teste standard / Standard tests		
	Frecventa de testare / Testing frequency Standard / Standard	Min Max
Densitate / Net density	Fiecare sarja / Each batch 3 masuratori pe sarja / 3 measurements per batch	EN ISO 845:2008 33.25 38.5
Duritate 40% / Hardness 40%	Fiecare sarja / Each batch	SR EN ISO 3386-1:2002/A1:2010 - -
Duritate 40% / Hardness 40%	Fiecare sarja / Each batch	SR EN ISO 2439:2008 118 162
Suport factor / Support factor	Fiecare sarja / Each batch	SR EN ISO 2439:2008 - -
Elasticitate / Elasticity	Fiecare sarja / Each batch	SR EN ISO 8307:2008 42 -
Rezistenta la tractiune / Tensile Strength	La 3 luni / Each 3 months	EN ISO 1798:2008 90 -
Alungire la rupere / Elongation at break	La 3 luni / Each 3 months	EN ISO 1798:2008 100 -
Rezistenta la compresiune 50% / Compression Set 50%	Fiecare sarja / Each batch	SR EN ISO 1856:2003/A1:2008 - 5
Teste pentru rezistenta la foc / Fire Resistance tests		
	ISO 13501	-
	FMVSS 302	-
	D451333	-
	BS 5852 (Crib5)	-
	FAR 25853 (aeronautic)	-
	TB 117-2013	-
Alte tipuri de teste / Others tests		
CertiPUR	CertiPur Standard	OK
OEKO-TEX	OEKO-TEX Standard 100	OK
TDA-MDA	IKEA IOS-MAT-0010	- 5
Pierdere inaltimii la oboseala / Thickness loss by fatigue	IKEA IOS-MAT-0076	- 5
Pierdere duritatii la oboseala / Hardness loss by fatigue	IKEA IOS-MAT-0076	- 32
Continutul de cenusa / Ash content	IKEA IOS-MAT-0076	- 2.75
Antistatizare / ESD Antistatic	ANSI/ESD S20.20; ANSI / ESD S541	-
Miros / Odor	NVX15012	-
Fum / Fogging	Method A (85%) DIN 75201	-
Imbatranire 2 / Aging 2	NVC00001	-
Dimethylfumarate (DMFu)	DIN CEN ISO TS16186	-
Recomandari de utilizare pentru industria mobilei / Recommended application		
Urmeaza sa fie testat To be tested	BS EN ISO 3385:2014	
Recomandari pentru roluire / Recommendations for rolling		
Sezon Cald / Warm Season		min. Ø 850
Sezon Rece / Cold Season		min. Ø 850
Tolerante standard blocuri / Standard tolerances of blocks		
Lungime / Length		-5 +15
Latime / Width		0 +100
Inaltime / Height		-100 +100

Nota:

Acest tip de spuma nu este tratat cu ignifugant.
Caracteristicile fizico-mecanice mentionate in prezenta specificatie tehnica constituie datele de calitate contractuala ale produsului la momentul transferului riscului si anume la predarea acestuia catre cumparator. Aceste caracteristici sunt controlate pentru fiecare sarja de produs si/sau la intervale regulate, ca parte a programului Eurofoam de asigurare a calitatii. Niciuna dintre aceste date si/sau proprietati nu reprezinta o garantie din punct de vedere juridic ca produsul este adecvat pentru un anumit scop sau utilizare si, in consecinta, Eurofoam isi declina orice responsabilitate rezultata din aceasta.

Note:

This type of foam is not treated with flame retardant.
The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing the risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of our can be derived therefrom.