



**FISA TEHNICA SPUMA POLIURETANICA**  
POLYURETHAN FOAM TECHNICAL DATA SHEET



Tip spuma (Foam grade):

**RF2828**

Caracteristici Characteristics	Frecventa testare Testing frequency	Standard Norm	Unitate de masura Measurement unit	Valoare Value	Toleranta Tolerance
Dimensiune bloc Dimension of block	-	-	mm	-	L = -5/+15 mm l = -0/+100 mm h = +/- 100 mm
Densitate Density	Fiecare sarja Each batch	ISO 845	kg/m <sup>3</sup>	28	-10+5%
Duritate 40% Hardness 40%	Fiecare sarja Each batch	ISO 3386-1	KPa	2.8	±10%
Rezistenta la tractiune Tensile Strength	La 6 luni Each 6 months	ISO 1798	KPa	90	min
Alungire la rupere Elongation at break	La 6 luni Each 6 months	ISO 1798	%	105	min
Elasticitate Resilience	Fiecare sarja Each batch	ISO 8307	%	30	min
Rezistenta la compresiune 50% Compression set 50%	La 6 luni Each 6 months	ISO 1856	%	12	max
Ignifugare Flammability	O data pe an Once per year	BS 5852 Crib5 FMVSS 302			
Culoare Colour	Gri, Alb, Negru Grey, White, Black				

**Nota:**

Caracteristicile fizico-mecanice mentionate in prezenta specificatie tehnica constituie datele de calitate contractuala ale produsului la momentul transferului riscului si anume la predarea acestuia catre cumparator. Aceste caracteristici sunt controlate pentru fiecare sarja de produs si/sau la intervale regulate, ca parte a programului Eurofoam de asigurare a calitatii. Niciuna dintre aceste date si/sau proprietati nu reprezinta o garantie din punct de vedere juridic ca produsul este adecvat pentru un anumit scop sau utilizare si, in consecinta, Eurofoam isi declina orice responsabilitate rezultata din aceasta.

**Note:**

The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing the risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of our can be derived therefrom.